

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization International Bureau



(43) International Publication Date
2 June 2005 (02.06.2005)

PCT

(10) International Publication Number
WO 2005/049330 A1

- (51) International Patent Classification⁷: **B41M 5/00**,
B32B 27/36, C08K 7/26
- (21) International Application Number:
PCT/EP2004/011896
- (22) International Filing Date: 21 October 2004 (21.10.2004)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
03/12953 5 November 2003 (05.11.2003) FR
- (71) Applicant (*for all designated States except US*): EASTMAN KODAK COMPANY [US/US]; 343 State Street, Rochester, NY 14650 (US).
- (72) Inventors; and
- (75) Inventors/Applicants (*for US only*): **FRIOUR, Gérard, Amédé, Désiré** [FR/FR]; Kodak Industrie, Département Brevets, CRT - Zone Industrielle, F-71102 Châlon sur Saône Cedex (FR). **EMONOT, Jérôme** [FR/FR]; Kodak Industrie, Département Brevets, CRT-Zone Industrielle, F-71102 Chalon sur Saone Cedex (FR). **PONCELET, Olivier, Jean, Christian** [FR/FR]; Kodak Industrie, Département Brevets, CRT - Zone Industrielle, F-71102 Châlon sur Saône Cedex (FR). **CAMPBELL, Bruce, Crinean** [US/US]; Eastman Kodak Company, Patent Department, 343 State Street, Rochester, NY 14650-2201 (US). **LANEY, Thomas, Miles** [US/US]; Eastman Kodak Company, Patent Department, 343 State Street, Rochester, NY 14650-2201 (US).
- (74) Agent: **HONORE, Anne-Claire**; Kodak Industrie, Département Brevets, CRT - Zone Industrielle, F-71102 Châlon sur Saône Cedex (FR).
- (81) Designated States (*unless otherwise indicated, for every kind of national protection available*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (*unless otherwise indicated, for every kind of regional protection available*): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

WO 2005/049330 A1

(54) Title: INKJET RECORDING ELEMENT

(57) Abstract: The present invention relates to an inkjet recording element having good dye keeping properties in time, good image quality, as well as instant dryness. Said inkjet recording element comprises a porous polyester support and at least one ink-receiving layer, said ink-receiving layer comprising at least one aluminosilicate polymer obtainable by a preparation method consisting in treating an aluminum halide with a mixture of at least one silicon alkoxide only having hydrolyzable substituents and at least one silicon alkoxide having a non-hydrolyzable substituent, with an aqueous alkali in the presence of silanol groups, the aluminum concentration being maintained less than 0.3 mol/l, the Al/Si molar ratio being maintained between 1 and 3.6 and the alkali/Al molar ratio being maintained between 2.3 and 3; and then stirring the resulting mixture at ambient temperature in the presence of silanol groups for long enough to form the hybrid aluminosilicate polymer. In addition, the ink-receiving layer does not contain a binder.